
Photonic Crystal Fibers by



# NL-2.3-790-02



Nonlinearity: 75 W<sup>-1</sup> km<sup>-1</sup>
Zero dispersion λ=790nm
Single material
Spliceable

# Highly nonlinear PCF

Our highly nonlinear photonic crystal fibers guide light in a small solid silica core, surrounded by a microstructured cladding formed by a periodic arrangement of air holes in silica. The optical properties of the core closely resemble those of a rod of glass suspended in air, resulting in strong confinement of the light and, correspondingly, a large nonlinear coefficient. By selecting the appropriate core diameter, the zero-dispersion wavelength can be chosen over a wide range in the visible and near infrared spectrum, making these fibers particularly suited to supercontinuum generation with Ti:Sapphire or diode-pumped Nd³+-laser sources.

#### Unique properties of Highly nonlinear PCF

- Zero dispersion wavelengths from 670-880 nm available
- Nonlinear coefficients up to 190 W<sup>-1</sup>km<sup>-1</sup> available (cf 1.1 W<sup>-1</sup>km<sup>-1</sup> for SMF 28 at 1550 nm)
- Near-Gaussian mode profile


#### **Applications**

- Supercontinuum generation for frequency metrology, spectroscopy or optical coherence tomography
- Four-wave mixing and self-phase modulation for switching, pulse-forming and wavelength conversion applications
- Raman amplification

To contact Crystal Fibre A/S, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com







Typical measured near field profile (log scale)

### **Optical properties**

•	Zero dispersion wavelength ( $\lambda_0$ )			790±5 nm
•	Dispersion slope at $\lambda_0$		0.64 p	os ·nm-² ·km-1
•	Attenuation	$\lambda_0$	<	25 dB/km
		1550 nm	<	15 dB/km
		1380 nm	<	100 dB/km
		1000 nm	<	17 dB/km
		600 nm	<	40 dB/km
•	Mode field diameter $^{\scriptscriptstyle 1}$ at $\lambda_0$			1.5±0.1 µm
•	Numerical aperture $^2$ at $\lambda_0$			0.4
•	Effective nonlinear area <sup>3</sup>			2.7 µm²
•	Nonlinear coefficient $^4$ at $\lambda_0$			75 W <sup>-1</sup> ·km <sup>-1</sup>

# **Physical properties**


•	Core diameter (average)	2.3±0.1µm
•	Pitch (distance between cladding holes)	1.6 µm
•	Air Filling Fraction in the holey region	>94%
•	Width of struts holding the core	70 nm
•	Diameter of holey region	35 µm
•	Diameter of outer silica cladding (OD)	147 µm
•	Coating diameter (single layer acrylate)	220 µm
•	Available length	up to 1 km

To contact Crystal Fibre A/S, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com







# Typical attenuation spectrum and chromatic dispersion



# **SEM** image of PCF region and core





To contact Crystal Fibre A/S, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com





#### **Notes**

- 1 Full 1/e-width of the near field intensity distribution
- 2 Sine of half angle at which a Gaussian fit to the far field intensity distribution has dropped to 1% of its peak value

$$A_{\text{eff}} = \frac{\left(\int\limits_{\infty} \left| \mathbf{E}(\mathbf{r}) \right|^2 d^2 \mathbf{r} \right)^2}{\int\limits_{\text{silica}} \left| \mathbf{E}(\mathbf{r}) \right|^4 d^2 \mathbf{r}}$$

$$\gamma = \frac{2\pi n_2}{A_{eff} \lambda}$$

$$n_2 \approx 2.5 \times 10^{-20} \text{ m}^2 \text{ W}^{-1} \text{ for silica}$$