


NL-2.6-830-02



Highly nonlinear PCF

Our highly nonlinear photonic crystal fibers guide light in a small solid silica core, surrounded by a microstructured cladding formed by a periodic arrangement of air holes in silica. The optical properties of the core closely resemble those of a rod of glass suspended in air, resulting in strong confinement of the light and, correspondingly, a large nonlinear coefficient. By selecting the appropriate core diameter, the zero-dispersion wavelength can be chosen over a wide range in the visible and near infrared spectrum, making these fibers particularly suited to supercontinuum generation with Ti:Sapphire or diode-pumped Nd³⁺-laser sources.

Nonlinearity: 54 W⁻¹ km⁻¹

Zero dispersion $\lambda=830\text{nm}$

Single material

Spliceable


Unique properties of Highly nonlinear PCF

- Zero dispersion wavelengths from 670-880 nm available
- Nonlinear coefficients up to 190 W⁻¹km⁻¹ available (cf 1.1 W⁻¹km⁻¹ for SMF 28 at 1550 nm)
- Near-Gaussian mode profile

Applications

- Supercontinuum generation for frequency metrology, spectroscopy or optical coherence tomography
- Four-wave mixing and self-phase modulation for switching, pulse-forming and wavelength conversion applications
- Raman amplification

To contact **Crystal Fibre A/S**, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com



Typical measured near field profile (log scale)

Optical properties

- Zero dispersion wavelength (λ_0) 830±5 nm
- Dispersion slope at λ_0 0.5 ps·nm⁻²·km⁻¹
- Attenuation


	λ_0	<	10 dB/km
	1550 nm	<	6 dB/km
	1380 nm	<	50 dB/km
	1000 nm	<	10 dB/km
	600 nm	<	20 dB/km
- Mode field diameter¹ at λ_0 1.8±0.1 μm
- Numerical aperture² at λ_0 0.38
- Effective nonlinear area³ 3.5 μm²
- Nonlinear coefficient⁴ at λ_0 54 W⁻¹·km⁻¹

Physical properties



- Core diameter (average) 2.6±0.1 μm
- Pitch (distance between cladding holes) 2.5 μm
- Air Filling Fraction in the holey region >86%
- Width of struts holding the core 150 nm
- Diameter of holey region 26 μm
- Diameter of outer silica cladding (OD) 127 μm
- Coating diameter (single layer acrylate) 220 μm
- Available length up to 1 km

To contact **Crystal Fibre A/ S**, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com

Typical attenuation spectrum and chromatic dispersion



SEM image of PCF region and core



To contact **Crystal Fibre A/S**, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com

Notes

- 1 Full 1/e-width of the near field intensity distribution
- 2 Sine of half angle at which a Gaussian fit to the far field intensity distribution has dropped to 1% of its peak value

$$3 \quad A_{\text{eff}} = \frac{\left(\int_{\text{silica}} |\mathbf{E}(\mathbf{r})|^2 d^2\mathbf{r} \right)^2}{\int_{\text{silica}} |\mathbf{E}(\mathbf{r})|^4 d^2\mathbf{r}}$$

$$4 \quad \gamma = \frac{2\pi n_2}{A_{\text{eff}} \lambda}$$

$n_2 \approx 2.5 \times 10^{-20} \text{ m}^2 \text{ W}^{-1}$ for silica

To contact **Crystal Fibre A/ S**, please visit our website www.crystal-fibre.com or send an email message to contact@crystal-fibre.com