NOTES:

1. SUBSTRATE

SAPPHIRE (AI2O3)

FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

2. SURFACE S2 TO BE PARALLEL WITH SURFACE S1 TO WITHIN ≤3.5 ARCMIN


3. COATING (APPLY ACROSS CLEAR APERTURE)


S1: NONE

S2: NONE

3. FINE GRIND SURFACE

- 4. POWER, IRREGULARITY, AND SURFACE QUALITY SPECIFICATIONS APPLY ACROSS CLEAR APERTURE
- 5. ROHS COMPLIANT





	S1	\$2]			FICATIONS SUBJECT TO CHANGE WITHOUT NOTICE
SHAPE	PLANO	PLANO				®
CLEAR APERTURE	Ø13.5	Ø13.5				[®] Edmund Optics [®]
SURFACE FLATNESS	2λ	2λ				
SURFACE ROUGHNESS	0.1 MICRONS PER INCH	0.1 MICRONS PER INCH		1		15mm DIAMETER UNCOATED, SAPPHIRE
SURFACE QUALITY	80-50	80-50	THIRD ANGLE PROJECTION	$\bigcirc \bigcirc$	TITLE	WINDOW
BIREFRINGENCE (n _o -n _e)	0.008	0.008		1		
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED	ALL DIMS IN	mm	DWG NO	43367 SHEET 1 OF 1