



## NOTES/SPECIFICATIONS:

CLEAR APERTURE: > \$\psi 45.72mm\$
SURFACE QUALITY: 40-20 SCRATCH-DIG
TRANSMITTED WAVEFRONT ERROR: <\lambda/4 AT 633nm
PARALLELISM: <3 arcmin
FILTER COATING (\$1):
REFLECTION BAND (R): >95% AVERAGE, >90% ABSOUTE 1000-1450nm
TRANSMISSION BAND (T): >90% AVERAGE, >85% ABSOLUTE 1550-2000nm
45° AOI
AR COATING (\$2):
R: <2% ABSOLUTE 1550-2000nm 45° AOI

FOR INFORMATION ONLY NOT FOR MANUFACTURING PURPOSES

DRAWING PROJECTION			THOR LABS.com		
	NAME	DATE	Ø 50.8mm LONGPASS		
DRAWN	MG	18/MAY/16	DICHROIC MIRROR 1500nm		1
APPROVAL	DD	08/JUNE/16	MATERIAL	$\sim$ $^{\wedge}$	RE'
COPYRIGHT © 2016 BY THORLABS			UV FUSED SILICA		Α
VALUES IN PARENTHESIS ARE CALCULATED AND MAY CONTAIN ROUNDOFF ERRORS			DMLP1500L	APPROX WEIGH	