

## NOTES:

1. SUBSTRATE:
VACUUM UV GRADE CaF2

- 2. SURFACE S2 TO BE PARALLEL WITH S1 TO < 1 ARCMIN
- 3. COATING (APPLY ACROSS CLEAR APERTURE) \$1 & \$2: R(ABS) ≤ 0.25% AT 880nm @ 0° AOI R(AVG) ≤ 1.25% FROM 400-870nm @ 0° AOI R(AVG) ≤ 1.25% FROM 890-1000nm @ 0° AOI







## FOR INFORMATION ONLY: DO NOT MANUFACTURE PARTS TO THIS DRAWING

SPECIFICATIONS SUBJECT TO CHANGE WITHOUT NOTICE DIMENSIONS ARE FOR REFERENCE ONLY

	\$1	\$2			R	Edmund Optics	<b>S</b> ®
SHAPE	PLANO	PLANO			W		<b>J</b>
SURFACE FLATNESS	λ	λ		1		25mm Dia., 1mm Thick, VIS-NIR Coated	·d
SURFACE QUALITY	40-20	40-20	THIRD ANGLE . PROJECTION	$\oplus \triangleleft$	TITLE	Calcium Fluoride Window	.α,
CLEAR APERTURE	Ø22.50	Ø22.50		 			CLIEFT
BEVEL	PROTECTIVE AS NEEDED	PROTECTIVE AS NEEDED	ALL DIMS IN	mm	DWG NO	22598	SHEET 1 OF 1